



# Polysurfacer ポリサフェーサー

FOR PROFESSIONAL USE ONLY

## 用途

2液型の速乾スプレーパテで、深い傷や凹みを充填するのに使用します。  
サンディング性に優れており、作業時間の短縮に役立ちます。

## 被塗物の前処理



温水と洗剤にて被塗物を洗浄し、洗浄後はきれいな水で洗剤を十分に洗い流してください。  
サンディング前に被塗物の不純物をシッケンズ脱脂剤にて除去してください。



ドライ P180-220 を使用して旧塗膜を剥離します。



ポリサフェーサー塗布前に被塗物の不純物をシッケンズ脱脂剤にて除去してください。

## 使用できる被塗物

スチール  
旧塗膜（硬化不良の塗膜やラッカー系塗膜はブロック塗装してください。）  
グラスファイバー  
プライマーサフェーサーEP（1コート / 最大 25.4µm）

※ポリサフェーサーはウォッシュプライマー1KCFの上に塗布してはいけません。

## 主剤と副剤

ポリサフェーサー

ポリサフェーサーハードナー

## 原材料


ポリキット IV : ポリエステル樹脂  
ハードナー : パーオキシサイド

## 使用前の攪拌



ご使用前にポリサフェーサーを充分攪拌して下さい。

## 混合比



100 部（容量比）      ポリサフェーサー  
5 部（容量比）        ポリサフェーサーハードナー



# Polysurfacer

## ポリサフェーサー

FOR PROFESSIONAL USE ONLY

**塗り重ね可能製品**

シッケンズ サフェーサー類で塗り重ね可能（オートサフェーサーWB は除く）

**塗装可能面積**

推奨する塗装方法で理論上の塗装可能面積：± 4 m<sup>2</sup> / リッター（混合済み）

実際の使用量については、被塗物の形状、表面の塗り肌の状況など塗装環境により異なります。

**器具の洗浄**

使用後はシンナーX 又はプラスリデューサーで速やかに洗浄して下さい。

**VOC 含有量**

245 g / L

**製品の保管**

製品の貯蔵安定期間は、20°Cで未開封の場合を基準としています。

※貯蔵安定期間については TDS S9.01.02 を参照してください。

**Akzo Nobel Car Refinishes**

Address: 510 Thomson Rd. #16-03 SLF Building Singapore 298135

Tel: +65-6254-8477

**FOR PROFESSIONAL USE ONLY**

**IMPORTANT NOTE** The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

**Head Office**

Akzo Nobel Car Refinishes B.V., PO Box 3 2170 BA Sassenheim, The Netherlands. [www.sikkenscr.com](http://www.sikkenscr.com)

